

Bioprinting Protocol

CELLINK BONE

This is a suggested procedure, please adjust according to your experimental needs. To maintain the sterility of the product work under sterile conditions.

Protocol aim

The aim of this protocol is to provide instructions for bioprinting with the CELLINK BONE using the INKREDIBLE, INKREDIBLE+, BIO X, or BIO X6. It covers the steps of pre-print mixing with cells, 3D bioprinting and post-print ionic crosslinking. Changing the parameters in the protocol might change printing pressure or the crosslinking time required. This protocol was optimized using the pneumatic printhead.

Materials needed

- CELLINK BONE*
- Crosslinking Agent*, included with the product
- Clear cartridges, 3cc*
- Sterile Conical Bioprinting nozzles, 22-25G recommended*
- BIO X*, BIO X6* or INKREDIBLE-series* 3D Bioprinter
- Well plate or Petri dish
- Cells + cell culture medium
- 3 mL syringes with Luer lock connections
- Female/female Luer lock adaptor*
- or
- CELLMIXER*

*The product can be purchased in the CELLINK store at www.cellink.com/store/.

Protocol

This protocol can be performed with printheads and print bed at room temperature, where room temperature is between 20-25°C.

Step	Title	Material	Description
1	Prepare bioink	- CELLINK BONE	<p>If not printing with cells move directly to step 3.</p> <p>The bioink should however ideally be mixed a few times anyway to remove possible mineral aggregation occurring during storage.</p> <ul style="list-style-type: none"> - Warm up the CELLINK BONE to room temperature.
2	Mix CELLINK BONE with cells	<ul style="list-style-type: none"> - 3 mL syringes with Luer lock connections - Prewarmed CELLINK BONE - Female/female Luer lock adaptor - Cell suspension in syringe 	<p>At this point, mix ten parts bioink with one part cell suspension, taking care not to introduce air bubbles to the mixture. For detailed instructions see the <i>Mixing Cells Protocol CELLINK Series</i>.</p> <ul style="list-style-type: none"> - Transfer the cell suspension to the 1 mL cell syringe (PART 1) using a female/female Luer lock adaptor. - Transfer the bioink to the 12 mL syringe (PART 2) using a female/female Luer lock adaptor. - Clip both syringes to the Dispensing unit (PART 3). - Connect the two syringes to the Mixing unit (PART 4), then connect the Empty cartridge (PART 5) to the Mixing units other side. - Apply gentle pressure onto the Dispensing unit to mix the content of both syringes into the empty cartridge. <p>Note: To avoid an air gap when mixing the bioink and the cell suspension, carefully pre-fill the Luer lock adaptor with CELLINK BONE before attaching the syringe with the cell suspension.</p> <p>If preparing for quantities < 2 mL of CELLINK BONE, it is recommended to connect two 3 mL Luer lock syringes and mix back and forth between the syringes until homogeneous.</p>
3	Load the cartridge	<ul style="list-style-type: none"> - Clear cartridges, 3cc loaded with CELLINK BONE (and cells) - Sterile Conical Bioprinting nozzles. 	<ul style="list-style-type: none"> - Place the room tempered CELLINK BONE in the printhead and cap with a printing nozzle of choice. <p>Note: Not recommended to use a nozzle with smaller diameter than 25G (such as 27G) due to risk of clogging.</p>
4	Printing	- Bioprinter (BIO X, BIO X6 or INKREDIBLE series recommended)	<ul style="list-style-type: none"> - Bioprint structures with parameters according to Table 1. If printability is not as desired, adjust the pressure up/down by 1 kPa to extrude more/less material.

	- Well plate or Petri dish	Note: If waiting too long between extrusions the bioink can dry in the nozzle causing it to clog. If this occurs, replace with new nozzle.
--	----------------------------	--

Table 1. Recommended minimal extrusion pressure** (± 2 kPa) used for printing continuous filaments at 20-25°C using diluted/undiluted bioink. 'Diluted' assumes a mixture of one part of PBS to ten parts of bioink, which is the simulation of bioink and cell suspension mixing conditions. For smaller dilutions, the pressure needs to be increased towards the pressure used for undiluted bioink.

Printing speed (mm/s) → Nozzle size (G) ↓	5	10	15	20
22	8	9	12	13
25	9	10	12	14

***This is only a recommended reference of starting pressures. The actual pressure needed for printing will vary depending on the preparation procedures (amount of bioink and actual temperature of the bioink) as well as the fitting of the piston in the cartridge and the leveling of the print surface. This table was generated with material temperature of 23°C.*

Step	Title	Material	Description
5	Crosslinking	- Crosslinking Agent - Cell culture medium	CELLINK BONE can be ionically crosslinked with CaCl ₂ -containing Crosslinking Agent. - Submerge the cell-laden constructs in the crosslinking solution for 30 seconds to 5 minutes depending on construct size. Remove crosslinking solution and rinse constructs with basal culture media once.
6	Incubation	- Cell culture medium	- After crosslinking and washing, add the desired medium to the constructs and place in incubator. - Incubate the constructs in cell culture medium in standard culture conditions (37°C, 5% CO ₂ and 95% relative humidity) or according to application.