

Specification Sheet

GelXG

Product description	GelXG is based on GelMA and incorporates xanthan gum to enhance printability at room temperature. GelXG can be crosslinked through photocuring. For description on how to mix with cells, bioprint and crosslink, follow the Bioprinting Protocol .
Intended use	Biocompatible material for 3D bioprinting, <i>Research Grade</i> . For research use ONLY. Not intended for <i>in vitro</i> diagnostics or <i>in vivo</i> uses. Not intended for administration in humans or animals. Produced under sterile and aseptic conditions.
Product number	IK3X0102
Shelf life	3 months, expiration date stated on package.
Storage and handling	Store at 4-8°C. DO NOT FREEZE. Avoid temperature fluctuations. Ensure that the bioink container is capped prior to storage to prevent drying. Protect from light.
Safety	Handle in accordance with good hygiene and laboratory safety practices. Read Safety Data Sheet for more information regarding ingredients and potential hazardous compounds.
Related documents	Bioprinting Protocol as well as Safety Data Sheet can be downloaded from our https://cellink.com/product/gelxg/ or scan the QR code below.



Property	Specifications	Method
<i>Appearance</i>	Semi-translucent gel	Visual inspection.
<i>Sterility</i>	Sterile	Tested for the presence of bacteria, fungi and yeast. Tested on raw material.
<i>Endotoxin level</i>	<30 EU/mL	Limulus Amoebocyte Lysate assay, Pharmacopoeia 2.6.14 "Bacterial endotoxins": Method D, accredited by SWEDAC. Accreditation Certification 1240: ISO 15189, 2010-11-22. Tested on raw material.
<i>Cell viability</i>	≥75% live cells	3D cell culture performed with mesenchymal stem cells for 7 days. Based on routine QC performed every fourth month.
<i>pH</i>	6.5-7.4	Assessed with pH meter.
<i>GelMA degree of methacrylation</i>	45-55%	¹ H NMR performed at room temperature, acquired with a spectral width of 8013 Hz, or 16 ppm, averaged over 64 scans using 64K time domain points. Acrylate peaks present at 5.4 and 5.6, methyl at 1.9 ppm.
<i>Viscosity</i>	1-1 000 Pa·s	Tested using rotational 20 mm plate-plate HR-2 TA Instruments Rheometer. Flow sweep parameters: shear rate from 0.002 s ⁻¹ to 500 s ⁻¹ , 25°C.