

Specification Sheet

GelMA A

Product description	GelMA A blends GelMA and alginate to combine cell compatibility and stability post-printing. Crosslink GelMA A through photoinitiator activation (LAP at 0.25% is already present in the bioink), or by a separate addition of the Crosslinking Agent. If only using ionic crosslinking, cell culture medium supplemented with calcium is required to maintain stability. Recommended for use with BIO X Temperature-controlled Printhead and cooled print bed, or for use with INKREDIBLE+ and heated printhead. For description on how to mix with cells, bioprint and crosslink, follow the Bioprinting Protocol .
Intended use	Biocompatible material for 3D bioprinting, <i>Research Grade</i> . For research use ONLY. Not intended for <i>in vitro</i> diagnostics or <i>in vivo</i> uses. Not intended for administration in humans or animals. Produced under sterile and aseptic conditions.
Product number	IK352102
Shelf life	Minimum 3 months, expiration date stated on package.
Storage and handling	Store at 4-8°C. DO NOT FREEZE. Protect from light and avoid temperature fluctuations. Ensure that the bioink container is capped prior to storage to prevent drying.
Safety	Handle in accordance with good hygiene and laboratory safety practices. Read Safety Data Sheet for more information regarding ingredients and potential hazardous compounds.
Related documents	Bioprinting Protocol as well as Safety Data Sheet can be downloaded from our website https://cellink.com/product/cellink-gelma-a or scan the QR code below.



<i>Property</i>	<i>Specification</i>	<i>Method</i>
<i>Appearance</i>	Semi-translucent gel	Visual inspection.
<i>Sterility</i>	Sterile	Tested for the presence of bacteria, fungi and yeast. Tested on raw material.
<i>Endotoxin level</i>	<50 EU/mL	Limulus Amoebocyte Lysate assay, Pharmacopoeia 2.6.14 "Bacterial endotoxins": Method D, accredited by SWEDAC. Accreditation Certification 1240: ISO 15189, 2010-11-22. Tested on raw materials.
<i>pH</i>	6.5-7.4	Assessed with pH paper.
<i>GelMA degree of methacrylation</i>	45-55%	¹ H NMR performed at room temperature, acquired with a spectral width of 8013 Hz, or 16 ppm, averaged over 64 scans using 64K time domain points. Acrylate peaks present at 5.4 and 5.6, methyl at 1.9 ppm.
<i>Viscosity</i>	30-150 Pa·s	Tested using rotational 20 mm plate-plate HR-2 TA Instruments Rheometer. Flow sweep parameters: shear rate from 0.002 s ⁻¹ to 500 s ⁻¹ , 22°C.